

SYDNEY

25 – 27 Green St
East Botany, NSW 2019
Ph: +61 2 9666 3788
Fax: +61 2 9666 4805

MELBOURNE

29 Trade Place
Vermont, VIC 3133
Ph: 03 9872 4033
Fax: 03 9872 4099

BRISBANE

Unit 6/5 Deakin Street
Brendale, QLD 4500
Ph: 07 3205 8510
Fax: 07 3205 9616

SINGAPORE

H.K. Moey
9 Elias Terrace
Singapore 519772
Ph: +65 6582 8103
Fax: +65 6584 8100
Mobile: +65 9751 0026



TECHNICAL DATA

Eracrete CB Release

RELEASE AGENT FOR CONCRETE MOULDING

ERACRETE CB RELEASE is a low viscosity liquid mould release agent based on a blend of vegetable oils and additives. It gives excellent release characteristics for simple and complex casting and moulding operations. It is recommended for use with moulds made from Erapol CC and CCM grades. This release agent is not recommended for use with moulds made from high performance, hot cast systems.

ERACRETE CB RELEASE is used for releasing of concrete based products from both flexible and rigid polyurethane moulds. It is designed for use at room temperature. Laboratory testing has shown that there is little effect on the polyurethane material and surface degradation.

APPLICATION

It is recommended that **ERACRETE CB RELEASE** be agitated before use.

Apply **ERACRETE CB RELEASE** to clean moulds by brushing or spraying. Drain excess release agent from the mould and air dry between 5 and 10 minutes. It may be necessary with virgin moulds to apply two coats of **ERACRETE CB RELEASE** to ensure there is a layer of release before pouring concrete.

For optimum surface results, lightly wipe/buff the inside of the mould with a clean, lint-free cloth after drying.

Periodically clean moulds to remove any dirt or build-up with either a mild soap detergent or caustic solution at ambient temperatures depending on the type of moulding material.

HANDLING PRECAUTIONS

Read the product material safety datasheet (MSDS) before use.

Use in well ventilated areas. Avoid breathing vapours or fumes. Avoid contact with skin and eyes. If contact occurs, wash immediately with soap and water.

This information is of general nature and is supplied without recommendation of guarantee. It does not make claim to be free from patent infringement. Properties shown are typical and do not imply specification tolerances. Era Polymers cannot accept liability for loss or damage through use. Whilst these technical details are based on expert knowledge, practical experience and laboratory testing, successful application depends upon the nature and conditions in which the products are supplied. Users must, by comprehensive testing, evaluate this product in their own application.

