

Sample No./Lot No. V0 - LXBMWT
 Client: Auralites

Table 1
 ASTM F2417-09
 Tea Light Cup Flammability Test

Sample	After Flame 1st 10 Sec. Exposure in Sec.	After Flame 2nd 10 Sec. Exposure in Sec.	Total Burn Time in Seconds	Comments
1	0	0	0	
2	0	0	0	
3	0	0	0	
4	0	1	1	
5	0	0	0	
6	0	0	0	
7	0	0	0	
8	0	1	1	
9	0	0	0	
10	0	1	1	
Total Burn	0	3	3	
Average			0.3	

Lab Temp: 73F
 Relative Humidity: 71%
 Test Date: 9/9/2009